

Square Loop Cores manufactured with cobalt-based METGLAS® amorphous alloy 2714A allow the design of mag amps that can operate at higher frequencies than previously possible. Their combination of magnetic properties enable magnetic amplifiers to provide unparalleled precision and efficiency in output regulation.

Mag amps are particularly well suited for outputs with currents of 1 amp to several tens of amps, although they are also used at lower currents where tight regulation and efficiency are extremely important.

Conventional regulated outputs are limited at higher frequencies and output currents. Linear regulators cannot handle output currents that exceed one or two amperes efficiently, and thus require heat sinking schemes, which increase the size of the power supply. Independent switched-mode sub-regulators avoid this inefficiency, but usually require circuitry which is more complex, expensive and less reliable than a mag amp.

Standard sizes are available from 9.6 mm to 34.1 mm OD and the possibility of manufacturing custom sizes also exists. Core coatings meeting UL94V-0 and temperature class F are available upon request.

Typical DC Hysteresis Loop METGLAS Alloy 2714A



METGLAS® Square Loop magnetic cores are specifically designed to exhibit an extremely square dc Hysteresis loop and high BSAT resulting in the following important benefits:

- Low saturated permeability
- Low coercive field – indicating a small reset current
- Low profile – enabling weight and volume reduction of up to 50%
- Low loss – resulting from micro-thin METGLAS® ribbon (18µm)

Physical Properties METGLAS® Alloy 2714A

| | |
|---------------------------------------|-------------------|
| Ribbon Thickness (µm) |18 |
| Density (g/cm ³) |7.59 |
| Thermal Expansion (ppm/°C) |12.7 |
| Crystallization Temperature (°C) |560 |
| Curie Temperature (°C) |225 |
| Continuous Service Temperature (°C) | <120 |
| Tensile Strength (MN/m ²) | 1k-1.7k |
| Elastic Modulus (GN/m ²) |100-110 |
| Vicker's Hardness (50g load) |960 |

Magnetic Properties METGLAS® Square Loop Cores

| | |
|-----------------------------------|---------------|
| Saturation Flux Density (Tesla) |0.57 |
| Saturation Magnetostriction (ppm) | <<1 |
| Electrical Resistivity (µ-Ω-cm) |142 |
| Squareness Ratio (%) | >95 |

**Core Loss vs. Flux Density†
@ 25°C**



B₈₀, B_r/B₈₀ vs. Temperature§



† B₈₀ - Flux Density @ 80 A/m

**Coercive Force vs. Frequency
@ 25°C**



Coercive Force vs. Temperature††



†† 1 Oe = 79.6 A/m

| MAGAMP COATED CORES | COATED CORE DIMENSIONS WITH OVALITY | | | CALCULATED SPECIFICATIONS | | | | BARE CORE | MAGNETIC SPECIFICATIONS | TEST SPECIFICATIONS | |
|------------------------|--|---------|---------|---------------------------|----------------------|------------------------------------|------------------------------------|--------------------------------------|----------------------------|---------------------|--|
| | Core Type | OD (mm) | ID (mm) | Ht (mm) | Lm ² (cm) | Ac ^β (cm ²) | Wa ^γ (cm ²) | WaAc ^x (cm ⁴) | Mass (g) | Bsat (T) | Squareness Ratio @ 5kHz / 0.5Oe, 4 Turns (Br/Bm) |
| | | (max) | (min) | (max) | (nom) | (nom) | (nom) | (nom) | (nom) | (nom) | (min) |
| MP1005M4AS | 11.37 | 5.91 | 6.12 | 2.59 | 0.06 | 0.27 | 0.02 | 1.20 | 0.57 | 84% | |
| MP1105M4AS | 12.50 | 8.76 | 6.29 | 3.24 | 0.03 | 0.60 | 0.02 | 0.77 | 0.57 | 84% | |
| MP1205M4AS | 13.30 | 7.77 | 6.29 | 3.14 | 0.06 | 0.47 | 0.03 | 1.39 | 0.57 | 84% | |
| MP1303M4AS | 14.32 | 8.76 | 4.70 | 3.50 | 0.04 | 0.60 | 0.02 | 1.12 | 0.57 | 84% | |
| MP1305M4AS | 14.07 | 8.76 | 6.29 | 3.46 | 0.06 | 0.60 | 0.03 | 1.53 | 0.57 | 84% | |
| MP1405M4AS | 15.54 | 8.76 | 6.29 | 3.67 | 0.08 | 0.60 | 0.05 | 2.35 | 0.57 | 84% | |
| MP1505M4AS | 16.87 | 8.76 | 6.29 | 3.87 | 0.11 | 0.60 | 0.06 | 3.17 | 0.57 | 84% | |
| MP1506M4AS | 16.80 | 8.76 | 7.87 | 3.86 | 0.14 | 0.60 | 0.08 | 4.18 | 0.57 | 84% | |
| MP1603M4AS | 17.58 | 11.86 | 4.70 | 4.50 | 0.04 | 1.10 | 0.05 | 1.43 | 0.57 | 84% | |
| MP1705M4AS | 18.75 | 11.86 | 6.29 | 4.66 | 0.08 | 1.10 | 0.09 | 2.95 | 0.57 | 84% | |
| MP1706M4AS | 18.73 | 11.86 | 7.87 | 4.68 | 0.11 | 1.10 | 0.12 | 4.07 | 0.57 | 84% | |
| MP1805M4AS | 20.25 | 11.86 | 6.29 | 4.88 | 0.11 | 1.10 | 0.12 | 4.10 | 0.57 | 84% | |
| MP1903M4AS | 21.24 | 11.86 | 4.70 | 5.00 | 0.08 | 1.10 | 0.09 | 3.17 | 0.57 | 84% | |
| MP1905M4AS | 20.29 | 11.86 | 6.29 | 4.92 | 0.11 | 1.10 | 0.12 | 4.29 | 0.57 | 84% | |
| MP1906M4AS | 20.97 | 11.86 | 7.87 | 4.99 | 0.16 | 1.10 | 0.18 | 6.23 | 0.57 | 84% | |
| MP2006M4AS | 21.81 | 14.33 | 7.87 | 5.54 | 0.12 | 1.61 | 0.20 | 5.20 | 0.57 | 84% | |
| MP2008M4AS | 21.86 | 11.86 | 9.91 | 5.15 | 0.25 | 1.10 | 0.27 | 9.88 | 0.57 | 84% | |
| MP2208M4AS | 23.69 | 15.57 | 9.91 | 6.01 | 0.18 | 1.90 | 0.33 | 8.16 | 0.57 | 84% | |
| MP2303M4AS | 24.91 | 15.57 | 4.70 | 6.19 | 0.08 | 1.90 | 0.15 | 3.88 | 0.57 | 84% | |
| MP2306M4AS | 25.13 | 15.57 | 7.87 | 6.23 | 0.17 | 1.90 | 0.32 | 8.16 | 0.57 | 84% | |
| MP2410M4AS | 26.30 | 18.05 | 11.05 | 6.83 | 0.21 | 2.56 | 0.53 | 10.91 | 0.57 | 84% | |
| MP2505M4AS | 27.43 | 18.05 | 6.29 | 7.01 | 0.12 | 2.56 | 0.32 | 6.75 | 0.57 | 84% | |
| MP2510M4AS | 27.47 | 18.05 | 11.05 | 7.01 | 0.25 | 2.56 | 0.64 | 13.50 | 0.57 | 84% | |
| MP2705M4AS | 29.10 | 15.57 | 6.29 | 6.89 | 0.21 | 1.90 | 0.39 | 11.03 | 0.57 | 84% | |
| MP3005M4AS | 32.01 | 18.05 | 6.29 | 7.69 | 0.21 | 2.56 | 0.53 | 12.30 | 0.57 | 84% | |
| MP3210M4AS | 34.72 | 21.14 | 11.05 | 8.58 | 0.39 | 3.51 | 1.36 | 25.78 | 0.57 | 84% | |
| MP3506M4AS | 37.43 | 24.24 | 7.87 | 9.52 | 0.25 | 4.61 | 1.15 | 18.35 | 0.57 | 84% | |

* α = Mean magnetic path length, β = Net Cross-sectional area, γ = Core Window area and x = Area product.

* All measurements are done at Room Temperature (22°C to 28°C)

* Continuous Operating Temperature : 90°C (max.).

* Ovality of 5% on outer and inner diameter is permissible.

* Powder coated core, minimum coating thickness of 0.076 mm (3 mils) is maintained on core surface.

* Powder Coating Material:-DuPont (EFB534S0) / Manufacturer UL File # E206123.

FM No. EG/FM/0023 Rev. No.: 0 Date: 12/May/15

| MAGAMP BOXED CORES | BOXED CORE DIMENSIONS | | | CALCULATED SPECIFICATIONS | | | | BARE CORE | MAGNETIC SPECIFICATIONS | TEST SPECIFICATIONS | | | | |
|-----------------------|-----------------------|---------|---------|---------------------------|--------------------|---------------------------------|----------------------------------|-----------|----------------------------|------------------------------------|----------|----------|--|-------|
| | Core Type (X) | OD (mm) | ID (mm) | Ht (mm) | Lm^{α} (cm) | Ac^{β} (cm ²) | Wa^{γ} (cm ²) | | | $WaAc^{\delta}$ (cm ⁴) | Mass (g) | Bsat (T) | Squareness Ratio @ 5kHz / 0.5Oe, 4 Turns (Br/Bm) | |
| | | (max) | (min) | (max) | (nom) | (nom) | (nom) | | | (nom) | | | (nom) | (nom) |
| MP1005X4AS | 11.20 | 5.30 | 6.00 | 2.59 | 0.06 | 0.25 | 0.01 | 1.20 | 0.57 | 86% | - | | | |
| MP1205X4AS | 14.10 | 6.50 | 6.90 | 3.14 | 0.06 | 0.36 | 0.02 | 1.39 | 0.57 | 86% | - | | | |
| MP1303X4AS | 15.00 | 7.60 | 5.40 | 3.50 | 0.04 | 0.49 | 0.02 | 1.12 | 0.57 | 86% | - | | | |
| MP1305X4AS | 14.70 | 7.60 | 7.00 | 3.46 | 0.06 | 0.49 | 0.03 | 1.53 | 0.57 | 86% | - | | | |
| MP1405X4AS | 16.10 | 7.60 | 7.00 | 3.67 | 0.08 | 0.49 | 0.04 | 2.35 | 0.57 | 86% | - | | | |
| MP1506X4AS / AH | 17.40 | 7.50 | 8.60 | 3.86 | 0.14 | 0.48 | 0.07 | 4.18 | 0.57 | 86% | 92% | | | |
| MP1603X4AS | 18.10 | 10.70 | 5.40 | 4.50 | 0.04 | 0.95 | 0.04 | 1.43 | 0.57 | 86% | - | | | |
| MP1805X4AS | 21.10 | 10.50 | 7.10 | 4.88 | 0.11 | 0.92 | 0.10 | 4.10 | 0.57 | 86% | - | | | |
| MP1903X4AS | 21.50 | 10.70 | 5.40 | 5.00 | 0.08 | 0.95 | 0.08 | 3.17 | 0.57 | 86% | - | | | |
| MP1906X4AS / AH | 21.50 | 10.70 | 8.60 | 4.99 | 0.16 | 0.95 | 0.15 | 6.23 | 0.57 | 86% | 92% | | | |
| MP2008X4AS / AH | 22.50 | 10.70 | 10.70 | 5.15 | 0.25 | 0.95 | 0.24 | 9.88 | 0.57 | 86% | 92% | | | |
| MP2303X4AS | 25.20 | 14.60 | 5.40 | 6.19 | 0.08 | 1.74 | 0.14 | 3.88 | 0.57 | 86% | - | | | |
| MP2410X4AS / AH | 28.10 | 17.00 | 11.80 | 6.83 | 0.21 | 2.35 | 0.48 | 10.91 | 0.57 | 86% | 92% | | | |
| MP2510X4AS / AH | 28.10 | 17.00 | 11.80 | 7.01 | 0.25 | 2.35 | 0.58 | 13.50 | 0.57 | 86% | 92% | | | |
| MP2705X4AS / AH | 29.80 | 14.50 | 7.00 | 6.89 | 0.21 | 1.72 | 0.36 | 11.03 | 0.57 | 86% | 92% | | | |
| MP3210X4AS / AH | 35.30 | 19.60 | 11.80 | 8.58 | 0.39 | 3.11 | 1.21 | 25.78 | 0.57 | 86% | 92% | | | |

* α = Mean magnetic path length, β = Net Cross-sectional area, γ = Core Window area and δ = Area product.

* All measurements are done at Room Temperature (22°C to 28°C)

* Continuous Operating Temperature :90°C max. (Irrespective of type of box used).

| BOX MATERIAL | BOX DESIGNATION (X) | MATERIAL DuPont | MANUFACTURER UL FILE # | MANUFACTURER FLAMMABILITY RATING |
|--------------|---------------------------|-----------------|---------------------------|--|
| | P | ZYTEL 70G33L | E41938 | HB |
| | L | ZYTEL FR50 | E41938 | 94 V0 |
| | V | RYNITE FR530L | E69578 | 94 V0 |

Contact Information:

AMERICAS

Hitachi Metals America LLC.

85 W. Algonquin Rd., Ste. 400
Arlington Heights, IL
60005-4142

Tel: (847) 364-7200 ext. 8219

Fax: (847) 364-7279 Fax

Компания «Life Electronics» занимается поставками электронных компонентов импортного и отечественного производства от производителей и со складов крупных дистрибьюторов Европы, Америки и Азии.

С конца 2013 года компания активно расширяет линейку поставок компонентов по направлению коаксиальный кабель, кварцевые генераторы и конденсаторы (керамические, пленочные, электролитические), за счёт заключения дистрибьюторских договоров

Мы предлагаем:

- Конкурентоспособные цены и скидки постоянным клиентам.
- Специальные условия для постоянных клиентов.
- Подбор аналогов.
- Поставку компонентов в любых объемах, удовлетворяющих вашим потребностям.
- Приемлемые сроки поставки, возможна ускоренная поставка.
- Доставку товара в любую точку России и стран СНГ.
- Комплексную поставку.
- Работу по проектам и поставку образцов.
- Формирование склада под заказчика.
- Сертификаты соответствия на поставляемую продукцию (по желанию клиента).
- Тестирование поставляемой продукции.
- Поставку компонентов, требующих военную и космическую приемку.
- Входной контроль качества.
- Наличие сертификата ISO.

В составе нашей компании организован Конструкторский отдел, призванный помогать разработчикам, и инженерам.

Конструкторский отдел помогает осуществить:

- Регистрацию проекта у производителя компонентов.
- Техническую поддержку проекта.
- Защиту от снятия компонента с производства.
- Оценку стоимости проекта по компонентам.
- Изготовление тестовой платы монтаж и пусконаладочные работы.



Тел: +7 (812) 336 43 04 (многоканальный)
Email: org@lifeelectronics.ru