
3MTM Shrinkable Tubing for Bus Bar BBI-A Series 5-35kV

Data Sheet March 2012



Description

3MTM Heat Shrinkable Tubing for Bus Bar BBI–A Series is designed for insulating rectangular, square and round bus barrated from 5 kV through 35 kV. It will also cover and insulate inline bolted connections of rectangular bus bars. The tubing meets the requirements of ANSI/IEEE Standard C37.20. The standard tubing lengths are 20 feet (6,1 m) and 50 feet (15,2m).

3M BBI—A Tubing is made of a specially formulated cross-linked polyolefin. The tubing is colored orange-red. The material has high resistance to splitting, good solvent resistance and excellent tracking resistance properties. The tubing shrinks easily with industry standard methods, forming an aesthetically appealing insulation cover.

Features

Specially formulated cross-linked polyolefin

- Excellent physical properties
- Excellent dielectric strength
- Excellent tracking resistance
- Excellent chemical resistance
- Good thermal endurance
- Flame retardant; self extinguishing
- Flexible; conforms to bends

Heat shrinkable design

- Each tube fits a range of bus bar sizes and voltage ratings
- Tight fit provides good heat dissipation



3MTM Heat Shrinkable Tubing for Bus Bar BBI-A Series 5-35 kV

Applications

For insulating electrical bus bars per ANSI/IEEE Standard C37.20:

- For 5, 8, 15, 25 and 35 kV voltage ratings
- For rectangular, square and round bus bars
- For inline bolted connections of rectangular bus bars
- For copper or aluminum bus bars
- For use in metal-clad switchgear
- For use on metal-enclosed bus bar
- For use with substation switchgear

Engineering/ Architectural Specifications

All straight sections of bus bar, and inline connections of rectangular bus bars, shall be insulated in accordance with the instructions included with the 3M Heat Shrinkable Tubing for Bus Bar BBI–A Series. This coverage shall include all copper and aluminum, rectangular, square and round bus bar's rated at 5, 8, 15, 25 and 35 kV.

Product Specifications

All straight sections of bus bar shall be insulated with 110°C (230°F) rated heat shrink tubing which meets the requirements of ANSI/IEEE C37.20. The tubing shall be made of halogen free, cross-linked polyolefin, orange-red in color. The tubing shall be rated for the same voltage rating as the bus bar, up to 35 kV. The insulation shall be designed for use on rectangular, square and round bus bars, and it must be designed to cover and insulate inline bolted connections of rectangular bus bars. The product must be packaged with complete installation instructions.

Performance Tests

Dielectric Withstand Tests (ANSI/IEEE C37.20):

Tests were performed on BBI Series Tubing installed on rectangular bus bar, on both straight sections and inline bolted connections. The 2 and 3 in. (51 and 76 mm) bars were 10 ft. (3,05 m) long, and all other bars were 12 ft. (3,66 m).

Power Frequency and Impulse Withstand Tests:

The samples were inserted through a grounded 3 ft. (0.9 m) long duct and positioned to required air gap clearance from one duct wall.

Test for Bus Bar Insulation:

The samples were wrapped with a half-lapped layer of Scotch® Electrical Shielding Tape 24 to establish a ground plane in contact with the BBI insulation.

Corona Tests (ANSI/IEEE 454):

Corona (partial discharge) testing was performed on BBI insulated bus bar which was inserted through a grounded 3ft. (0.9 m) long duct. The bar was positioned to the required air gap clearance from one duct wall. The test results suggest that the air gap between the bar and duct is so large in relationship to the air gap between the bar and insulation, that no corona condition exits in the normal testing range up to 38 kV.

Typical Physical and Electrical Properties	
* All values are averages, based on several determinations,	
and are not intended for specification purposes	
Electrical Properties	
Test Method	Typical Value*
Dielectric Constant	
(ASTM D-150)	3.5
Dielectric Strength (70 mils)	550 V/mil
(ASTM D-149)	(22 MV/m)
Volume Resistivity	(22 111 7/11)
(ASTM D-257)	1.4×10^3
(MIL-I-23053/15A)	
Track Resistance (7 hrs.)	1: 005111
(ASTM D–2303)	1 in. @ 2.5 kV
(ANSI/IEEE C37.20)	(25mm @ 2.5 kV)
Physical Properties	
Test Method	Typical Value*
Tensile Strength	
(ASTM D-257)	2200 psi
(MIL-I-23053/15A)	(15 MPa)
Ultimate Elongation	
(ASTM D-638)	575%
(MIL-I-23053/15A)	
Water Absorption	1
7 days @ 23°C (73°F)	0.3%
(MIL-I-23053/15A)	
Corrosion (Copper)	
16 hrs. @ 120°C (248°F)	Pass
(MIL-I-23053/15A)	
Fluid Resistance	Tensile = 810-2400 psi (5.6-16.5 MPa)
24 hrs. immersed	
(MIL-I-23053/15A)	Dielectric Str. = 287–451 V/mil (11.3–17.8 MV/m)
Thermal Properties	
Test Method	Typical Value*
Flammability	Pass
(ANSI/EEE C37.20)	1 000
Thermal Endurance	110° C (230° F)
(ANSI/EEE 1) (IEC 216)	` '
Accelerated Aging	Tensile = 1430 psi (10 MPa)
7 days @ 175° C (347° F)	
(MIL-I-23053/15A)	Elongation = 400%
Heat Shock	_
4 hrs @ 225° C (437° F)	Pass
(MIL-I-23053/15A)	_
Low Temperature Flexibility	_
4 hrs @ -55° C (-67° F)	Pass
(MIL-I-23053/15A)	

.

Fluid Resistance (MIL-I-23053/15A) Immersion at 23° C (73° F) for 24 hours

	Typical Physical Properties after Immersion						
Fluid	Fluid Absorption (% by wt.)	Tensile Strength (ps) (MPa)	Elongation at Break (%)	Dielectric Strength (V/mil @ 0.150 in.) (MV/m)	Results		
Specification		>750		>200			
Requirement Deicing fluid (Mil-A-8243)	0.0	(> 5,2) 2330 (16,1)	600	(> 7,9) 333 (13,1)	Pass		
Hydraulic fluid (Mil-H-5606)	2.8	1920 (13,2)	550	392 (15,4)	Pass		
Lube oil (Mil-L-7808)	0.8	2330 (16,1)	515	404 (15,90	Pass		
Lubricating oil (Mil-T-5624)	0.3	2365 (16,3)	515	451 (17,8)	Pass		
Jet fuel, JP-4 (Mil-T-5624)	7.4	1380 (9,5)	515	349 (13,7)	Pass		
5% Salt water	0.1	2400 (16,5)	525	436 (17,2)	Pass		
30% Ammonia solution	0.4	2175 (15,0)	600	403 (15,9)	Pass		
Noalox Joint Compound	0.4	2180 (15,0)	515	439 (17,3)	Pass		
Contact cleaner (3M #1607)	42.0	830 (5,70	385	287 (11,03)	Pass		
Black enamel Paint	23.1	810 (5,6)	350	366 (14,4)	Pass		
Acetone	4.2	1550 (10,7)	510	339 (13,3)	Pass		
Methylene Chloride	37.9	900 (6,2)	340	313 (12,3)	Pass		

3M™ Heat Shrinkable Tubing for Bus Bar BBI-A Series 5-35 kV


Test Description	Rated Maximum Voltage (kV)	ANSI/IEEE C37.20 REQURIEMENT (Kv)	Typical Maximum results (kV)
Power Frequency	8.25	26	> 50 (@ 2.5")
	15.50	50	> 50 (@ 2.5")
1 Minute Withstanding	25.80	60	> 60 (@ 2.5")
(Duct application)	38.00	80	> 80 (@ 5.5")
Bus Bar Insulation 1 Minute Withstand (shielding tape application)	8.25	8.25	20
	15.50	15.50	20
	25.80	25.80	35
	38.00	38.00	50
Impulse Withstand (1.2 x 50 us wave)	8.25	75	±125 (@ 2.5")
	15.50	110	±125 (@ 2.5")
	25.80	125	±130 (@ 3.5")
	38.00	150	±165 (@ 5.5")

Typical Corona Values						
Rated Maximum Voltage kV	Air Gap (to duct) (in.)	Typical Corona Starting Voltage (CSV) (kV @ > 3pc)	Typical Corona Extinction Voltage (CSV) (kV @ > 3pc)			
8.2	2.5	40	38			
15.50	2.5	40	38			
25.80	3.5	45	42			
38.00	5.5	45	42			

3MTM Heat Shrinkable Tubing for Bus Bar BBI-A Series 5-35 kV

 $3M^{TM}$ Heat Shrinkable Tubing for Bus Bar BBI–A can be used on bus bar rated up to $110^{\circ}C(230^{\circ}F)$, for 5, 8, 15, 25 and 35 kV voltage classes.

Selection Charts for Straight Bus Bar Standard lengths = 20ft. (6.1mm) and 50ft. (15.2mm)







				/		
5, 8 and	15 kV Bus Bar	Size Ranges				
Product	Bar					
Number	Circumference	→				
Namber	(A)	Rectangular*	Square*	Round		
BB1-3A	3.28 – 5.57 in.	1 1/2 x 1/4 – 2 1/2 x 1/2 in.	1 x 1 – 1 1/2 x 1 1/2 in.	1 1/8 – 1 3/4 in.		
	(83 – 141 mm) 5.43 – 8.86 in.	(38 x 6 – 64 x13 mm) 2 1/2 x 3/8 – 4 x 3/4 in.	(25 x 25 – 38 x 38 mm) 2 x 2 in.	(25 – 44 mm) 1 3/4 – 2 3/4 in.		
BB1-4A	5.43 – 8.86 in. (138 – 225 mm)	(64 x 10 – 102 x19 mm)	2 x 2 in. (51 – 51 mm)	(44 – 70 mm)		
BB1-5A	6.67 – 10.86 in.	3 x 5/8 – 5 x 3/4 in.	2 x 2 – 2 1/2 x 2 1/2 in.	2 1/8 – 3 3/8 in.		
BB1-3A	(169 – 276 mm)	(76 x 16 – 127 x19 mm)	(51 x 51 – 64 x 64 mm)	(54 – 86 mm)		
BB1-6A	7.57 – 12.86 in.	3 1/2 x 1/2 – 6 x 3/4 in.	2 1/2 x 2 1/2 – 3 x 3 in.	2 1/2 – 4 in.		
	(192 – 327 mm) 8.28 – 13.00 in.	(89 x 13 – 152 x19 mm) 4 x 1/4 – 6 x 3/4 in.	(64 x 64 – 76 x 76 mm) 2 1/2 x 2 1/2 – 3 x 3 in.	(64 – 102 mm) 2 3/4 – 4 1/8 in.		
BB1-7A	(210 – 330 mm)	(102 x 6 – 152 x19 mm)	(64 x 64 – 76 x 76 mm)	(70 – 105 mm)		
DD4 04	10.29 – 16.43 in.	5 x 1/4 – 8 x 3/8 in.	3 x 3 – 4 x 4 in.	3 3/8 – 5 1/8 in.		
BB1-8A	(261 – 417 mm)	(127 x 6 – 203 x 10 mm)	(76 x 76 – 102 x 102 mm)	(86 – 130 mm)		
BB1-9A	12.29 – 19.23 in.	6 x 1/4 – 9 x 3/4 in.	3 1/2 x 3 1/2 – 5 x 5 in.	4 – 6 1/8 in.		
DD1-3A	(312 – 488 mm)	(152 x 6 – 229 x 19 mm)	(89 x 89 – 127 x 127 mm)	(102 – 156 mm)		
BB1-10A	15.43 – 24.14 in. (392 – 613 mm)	8 x 1/4 – 10 x 3/4 in. (203 x 6 – 254 x 19 mm)	5 x 5 – 6 x 6 in. (127 x 127 – 152 x 152 mm)	5 – 7 5/8 in. (127 – 194 mm)		
25 kV B	us Bar Size Ran	,	(121 x 121 - 132 x 132 11111)	(127 – 194 11111)		
	3.28 – 5.57 in.	1 1/2 x 1/4 – 2 1/2 x 1/2 in.	MEASURE	1 1/8 in.		
BB1-3A	(83 – 141 mm)	(38 x 6 – 64 x13 mm)	CIRCUMFERENCE	(29 mm)		
BB1-4A	5.43 – 8.86 in.	2 1/2 x 3/8 – 4 x 3/4 in.	MEASURE	1 ¾ in.		
1001-44	(138 – 225 mm)	(64 x 10 – 102 x19 mm)	CIRCUMFERENCE	(44 mm)		
BB1-5A	6.67 – 10.86 in.	3 x 5/8 – 5 x 3/4 in.	MEASURE	2 1/8 – 2 1/4 in.		
	(169 – 276 mm) 7.57 – 12.86 in.	(76 x 16 – 127 x19 mm) 3 1/2 x 1/2 – 6 x 3/4 in.	CIRCUMFERENCE MEASURE	(54 – 57 mm) 2 1/2 – 2 5/8 in.		
BB1-6A	(192 – 327 mm)	(89 x 13 – 152 x19 mm)	CIRCUMFERENCE	(64 – 67 mm)		
BB1-7A	8.28 – 13.00 in.	4 x 1/4 – 6 x 3/4 in.	2 1/2 x 2 1/2 in.	2 3/4 – 3 1/4 in.		
DD I-7A	(210 – 330 mm)	(102 x 6 – 152 x19 mm)	(64 x 64 mm)	(70 – 83 mm)		
BB1-8A	10.29 – 16.43 in.	5 x 1/4 – 8 x 3/8 in.	3 x 3 in.	3 3/8 – 4 in.		
	(261 – 417 mm) 12.29 – 19.23 in.	(127 x 6 – 203 x 10 mm) 6 x 1/4 – 9 x 3/4 in.	(76 x 76 mm) 3 1/2 x 3 1/2 – 4 x 4 in.	(86 – 102 mm) 4 – 4 7/8 in.		
BB1-9A	(312 – 488 mm)	(152 x 6 – 229 x 19 mm)	(89 x 89 – 102 x 102 mm)	4 – 4 7/8 in. (102 – 124 mm)		
	15.43 – 24.14 in.	8 x 1/4 – 10 x 3/4 in.	5 x 5 in.	5 – 6 1/4 in.		
BB1-10A	(392 – 613 mm)	(203 x 6 – 254 x 19 mm)	(127 x 127 mm)	(127 – 194 mm)		
35 kV Bus Bar Size Ranges						
BB1-7A	8.28 – 8.86 in.	4 x 1/4 – 4 x 3/4 in.	MEASURE	2 3/4 in.		
DD I-7A	(210 – 225 mm)	(102 x 6 – 102 x19 mm)	CIRCUMFERENCE	(70 mm)		
BB1-8A	10.29 – 10.94 in. (261 – 278 mm)	5 x 1/4 – 5 x 3/4 in. (127 x 6 – 127 x 19 mm)	MEASURE CIRCUMFERENCE	3 3/8 in. (86 mm)		
	(261 – 278 mm) 12.29 – 13.00 in.	6 x 1/4 – 6 x 3/4 in.	MEASURE	(86 mm) 4 – 4 1/8 in.		
BB1-9A	(312 – 330 mm)	(152 x 6 – 152 x 19 mm)	CIRCUMFERENCE	(102 – 105 mm)		
DD1 101	15.43 – 16.86 in.	8 x 1/4 – 8 x 3/4 in.	MEASURE	5 – 5 1/4 in.		
BB1-10A	(392 – 428 mm)	(203 x 6 – 203 x 19 mm)	CIRCUMFERENCE	(127 – 133 mm)		

NOTE:* Rectangular and square bar sizes are based on bars having radiused edges and corners.

NOTE: BBI–A tubing sizing is based on straight sections of bar. For bolted connections consult bolted connection chart on page 3.

NOTE: Contact your 3M sales rep for recommendation on the use of BBI-A on 1/8" thick bus bar.


3M[™] Heat Shrinkable Tubing for Bus Bar BBI–A Coverage for Inline Bolted Connections (Rectangular Bus Bar) Note: First slect BB1-A size form preceding charts for Straight Bus Bar 5, 8 & 15kV: Inline Bolted Connections

5, 6 & 15kV. Illillie Bolled Collifections								
Rectangular Bar Width	BBI-3A	BBI-4A	BBI-5A	BBI-6A	BBI-7A	BBI-8A	BBI-9A	BBI-10A
1.5 in. (38 mm)	1 Layer							
2.0 in. (51 mm)	2 Layer							
2.5 in. (64 mm)		1 Layer						
3.0 in. (76 mm)		2 Layer						
3.5 in. (102 mm)		2 Layer	1 Layer					
4.0 in. (127 mm)		2 Layer	2 Layer	1 Layer	1 Layer			
5.0 in. 152 mm)			2 Layer	2 Layer	1 Layer	1 Layer		
6.0 in. (178 mm)				2 Layer	2 Layer	1 Layer	1 Layer	
7.0 in. (203 mm)						2 Layer	1 Layer	
8.0 in. (229 mm)						2 Layer	2 Layer	1 Layer
9.0 in. (254 mm)							2 Layer	1 Layer
10.0 in. (254 mm)								2 Layer

25 & 35 kV: Inline Bolted Connections USE 2 LAYERS OF BBI-A TUBING FOR ALL 25 & 35 kV Inline Bolted Connections

Typical Dimensions							
Product Number	Length	Minimum Expanded Tubing I. D.	Expanded Wall Thickness	Max. Recovered Tubing I. D.	Recovered Wall Thickness		
BB1-3A	20 & 50 ft	2.38 in.	0.049 in.	1.01 in.	0.113 in.		
	(6.1 & 15.2 mm)	(60 mm)	(1,24 mm)	(26 mm)	(2,87 mm)		
BB1-4A	20 & 50 ft	4.35 in.	0.043 in.	1.67 in.	0.113 in.		
	(6.1 & 15.2 mm)	(110 mm)	(1,09 mm)	(42 mm)	(2,87 mm)		
BB1-5A	20 & 50 ft	5.30 in.	0.043 in.	2.04 in.	0.114 in.		
	(6.1 & 15.2 mm)	(135 mm)	(1,09 mm)	(52 mm)	(2,90 mm)		
BB1-6A	20 & 50 ft	5.90 in.	0.046 in.	2.33 in.	0.117 in.		
	(6.1 & 15.2 mm)	(150 mm)	(1,17 mm)	(59 mm)	(2,97 mm)		
BB1-7A	20 & 50 ft	6.78 in.	0.048 in.	2.55 in.	0.130 in.		
	(6.1 & 15.2 mm)	(172 mm)	(1,22 mm)	(65 mm)	(3,30 mm)		
BB1-8A	20 & 50 ft	8.25 in.	0.049 in.	3.18 in.	0.128 in.		
	(6.1 & 15.2 mm)	(210mm)	(1,24 mm)	(81 mm)	(3,25 mm)		
BB1-9A	20 & 50 ft	8.83 in.	0.054 in.	3.78 in.	0.127 in.		
	(6.1 & 15.2 mm)	(224 mm)	(1,37 mm)	(96 mm)	(3,23 mm)		
BB1-10A	20 & 50 ft	10.28 in.	0.059 in.	4.53 in.	0.138 in.		
	(6.1 & 15.2 mm)	(261 mm)	(1,50 mm)	(115 mm)	(3,51 mm)		

Typical Clearances for Rectangular and Square Bus Bars



Voltage Rating	BIL		nsulated Elearance)		ated learance)	
(kV)	(Kv)	Dimension	Dimension	Dimension	Dimension	
		b	С	b	С	
15 & Below 110	110	2.7 in.	3.0 in.	7.5 in.	5.0 in.	
	110	(69 mm)	(76 mm)	(191 mm)	(127 mm)	
25	125	3.0 in.	3.5 in.	10.5 in.	7.5 in.	
25 12	125	(76 mm)	(89 mm)	(267 mm)	(191 mm)	
35	150	4.5 in.	5.5 in.	12.5 in.	9.5 in.	
33	130	(114 mm)	(140 mm)	(318 mm)	(241 mm)	

NOTE: b = minimum phase—to—phase dimension c = minimum phase—to—ground dimension

The table indicates typical minimum clearance dimensions for 3MTM Heat Shrinkable Tubing for Bus Bar BBI–A as compared to that for uninsulated bus bar. These dimensions are based on 60 Hz withstand, DC withstand (hypot) and BIL tests (Reference: ANSI/IEEE C37.20) and from partial discharge (corona) tests. Testing was performed on 12 ft. (3,7 m) lengths of copper and aluminum bus bar enclosed in a 3 ft. (0,9 m) long duct, with air spacing between the bar and grounded duct.

Application Tips

- 1. Keep Torch flame moving to prevent burning.
- **2.** For rectangular bars: Shrink the edges of the BBI–A tubing first. This will achieve a more uniform insulation thickness around the bar.
- **3.** BBI–A tubing normally shrinks at approx. 250_F(120_C). (Caution: burn damage can occur if tubing temperature exceeds approx. 600_F (315_C) for several minutes.)
- **4.** Dimples appearing in BBI–A tubing during shrinkage are normal, and are removed with continued even heating.
- **5.** Heat application should be discontinued immediately after dimples disappear, or when tubing has shrunk smoothly onto bar.
- 6. Use proper torch which produces a blue and yellow flame.
- 7. CAUTION: Be careful handling insulated bus bar while it is still hot. The heated tubing is soft and susceptible to physical damage.
- **8.** SAFETY: Use caution and proper safety procedures when working with open flame and high temperatures. This would include maintaining a well ventilated workplace.


Installation Techniques

An instruction sheet is included in each package to provide the installer with the information required to properly install the 3MTM Heat Shrinkable Tubing on bus bar. A brief summary of the installation for BBI–A is outlined as follows:


Instructions for Straight Bus Bar

- 1. Clean bus bar and cut BBI–A Tubing to required length. Use a sharp knife or razor to ensure a clean cut with no nicks.


 Preheat
- 2. Preheating of bus bar is recommended.
- 3. Slide BBI-A Tubing into position and shrink onto busbar using standard industry methods.



Instructions for Inline Bolted Connections




- 1. For 15 kV applications consult the Inline Bolted Connections chart on page 3. Determine whether one or two layers of BBI–A will be required. All 25 and 35 kV applications will require two layers of BBI–A (see Additional Instructions for 25 and 35 kVConnections on page 7).
- 2. Clean the bolted connection.
- **3.** Cut one layer of BBI–A tubing to cover at 6 inches (152 mm) of existing insulation on each side of the connection. Exercise care to ensure a clean cut.
- **4.** Cut a second (outer) layer of BBI–A tubing (if required) to a length that is 2 inches (51 mm) shorter than the first layer.
- **5.** Shrink the first (inner) layer of BBI–A tubing onto the bus bar and bolted connection. If required, center the second layer of tubing over the first layer and shrink using standard industry methods.



Additional Instruction for 25 and 35 kV Connections

1. Fill in edges of existing bus bar insulation with an electrical grade filler before applying two layers of BBI–A tubing.



Maintenance

3MTM Heat Shrinkable Tubing for Bus Bar BBI–A is not impaired by freezing or overheating due to ambient temperatures found in storage or shipping. Normal storage and stock rotation practices are recommended.

Shelf Life & Storage

This product has a 10-year shelf life from date of manufacture when stored in a humidity controlled storage (10°C/50°F to 27°C/80°F and <75% relative humidity).

Availability

Please contact your local distributor; available from 3M.com/electrical {Where to Buy} or call 1-800-245-3573.

IMPORTANT NOTICE

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product, which are not contained in 3M's current publications, or any contrary statements contained on your purchase order, shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M

Warranty; Limited Remedy; Limited Liability

This product will be free from defects in material and manufacture at the time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.

3M and Scotch are trademarks of 3M Company.



Electrical Markets Division 6801 River Place Blvd. Austin, TX 78726-9000 800.245.3573 FAX: 800.245.0329 www.3M.com/electrical

Please recycle © 3M 2012 All rights reserved 78-8141-4993-2



OOO «ЛайфЭлектроникс" "LifeElectronics" LLC

ИНН 7805602321 КПП 780501001 P/C 40702810122510004610 ФАКБ "АБСОЛЮТ БАНК" (ЗАО) в г.Санкт-Петербурге К/С 3010181090000000703 БИК 044030703

Компания «Life Electronics» занимается поставками электронных компонентов импортного и отечественного производства от производителей и со складов крупных дистрибьюторов Европы, Америки и Азии.

С конца 2013 года компания активно расширяет линейку поставок компонентов по направлению коаксиальный кабель, кварцевые генераторы и конденсаторы (керамические, пленочные, электролитические), за счёт заключения дистрибьюторских договоров

Мы предлагаем:

- Конкурентоспособные цены и скидки постоянным клиентам.
- Специальные условия для постоянных клиентов.
- Подбор аналогов.
- Поставку компонентов в любых объемах, удовлетворяющих вашим потребностям.
- Приемлемые сроки поставки, возможна ускоренная поставка.
- Доставку товара в любую точку России и стран СНГ.
- Комплексную поставку.
- Работу по проектам и поставку образцов.
- Формирование склада под заказчика.
- Сертификаты соответствия на поставляемую продукцию (по желанию клиента).
- Тестирование поставляемой продукции.
- Поставку компонентов, требующих военную и космическую приемку.
- Входной контроль качества.
- Наличие сертификата ISO.

В составе нашей компании организован Конструкторский отдел, призванный помогать разработчикам, и инженерам.

Конструкторский отдел помогает осуществить:

- Регистрацию проекта у производителя компонентов.
- Техническую поддержку проекта.
- Защиту от снятия компонента с производства.
- Оценку стоимости проекта по компонентам.
- Изготовление тестовой платы монтаж и пусконаладочные работы.



Тел: +7 (812) 336 43 04 (многоканальный) Email: org@lifeelectronics.ru