

CUSTOMER DRAWING

Slit Adhesive Sleeve (S-1017)




Table 1: Dimensions (inches)

| PART DESCRIPTION | EXTRUDED ID (A) | CUT LENGTH (B) | EXTRUDED WALL (C) |
|------------------|--------------------|-------------------|----------------------|
| SAS-090-038-1017 | .090 ± .005 | 0.38 ± .050 | 0.024 ± .005 |
| SAS-090-075-1017 | .090 ± .005 | 0.75 ± .050 | 0.024 ± .005 |
| SAS-090-1-1017 | .090 ± .005 | 1.00 ± .050 | 0.024 ± .005 |
| SAS-115-075-1017 | .115 ± .005 | 0.75 ± .050 | 0.032 ± .005 |
| SAS-115-1-1017 | .115 ± .005 | 1.00 ± .050 | 0.032 ± .005 |
| SAS-160-075-1017 | .160 ± .005 | 0.75 ± .050 | 0.032 ± .005 |
| SAS-160-1-1017 | .160 ± .005 | 1.00 ± .050 | 0.032 ± .005 |
| SAS-200-075-1017 | .200 ± .005 | 0.75 ± .050 | 0.035 ± .005 |
| SAS-200-1-1017 | .200 ± .005 | 1.00 ± .050 | 0.035 ± .005 |

Color: Amber

| | | | | | | |
|--|--|--|-------------------------|--|--------------------------|--|
| | | Tyco Electronics Corp. 300 Constitution Drive, Menlo Park, CA. 94025 | Raychem Molded Parts | TITLE: SPLIT ADHESIVE SLEEVE | | |
| Unless otherwise specified, dimensions are in inches. [Metric dimensions are shown in brackets] | | | | DOCUMENT NO.: SAS-XXX-XXX-1017 | | |
| TOLERANCES: 0.00 N/A 0.0 N/A 0 N/A | ANGLES: N/A ROUGHNES S IN MICRON | Tyco Electronics reserves the right to amend this drawing at any time. Users should evaluate the suitability of the product for their application. | | REVISION: D | DATE: August 14, 2008 | |
| PREPARED BY: UNGUYEN | ECO NUMBER: ECO-08-020204 | CAGE CODE : 06090 | SCALE: -NA- | SIZE: A | SHEET: 1 of 3 | |

© 2004 –2008 Tyco Electronics Corporation. All rights reserved.

If this document is printed it becomes uncontrolled. Check for the latest revision.

CUSTOMER DRAWING

Table 2: Properties

| Property | Unit | Requirements | Test Method |
|--|--------------|--|-------------|
| Physical | | | |
| Visual | -- | No foreign matter, voids, pinholes. | |
| Specific Gravity | -- | 0.95 ± 0.05 | ASTM D 792 |
| Softening Point | °C | 120 ± 10 | ASTM E 28 |
| Low Temperature Impact Brittleness | °C | -20 maximum | ASTM D 746 |
| Adhesive Peel Polyolefin Polychloroprene Polyvinylchloride | lbs/in width | 20 minimum 10 minimum 15 minimum | Note 1 |
| Chemical* | | | |
| Water Absorption | Percent | 1.0 maximum | ASTM D 570 |
| Fungus Resistance | -- | Rating of 1 or less | ASTM G 21 |
| Fluid Resistance* Weight Change after 7 days/23 ± 3°C (75 ± 5°F) 3 X 1-inch specimens Detergent Solution (#12) Hydraulic Fluid (MIL-PRF-87257 or MIL-PRF-83282) Lube Oil (MIL-PRF-7808L) ASTM Oil (#49) | Percent | 3 maximum 10 maximum 5 maximum 15 maximum | ASTM D 543 |
| Electrical* | | | |
| Volume Resistivity | ohm-cm | 10 ¹⁰ minimum | ASTM D 257 |
| Dielectric Strength | V/mil | 500 minimum | ASTM D 149 |

*Test specimens shall be prepared in the form of 6 x 6 x .075-inch compression molded slabs. Molding temperature shall be 150 ± 3°C (302 ± 5°F).

Acceptance Tests: Visual, Dimensions, Specific Gravity

| | | | | |
|--|------------------------------|------------|--------------------------|------------------|
| DOCUMENT NO.: SAS-XXX-XXX-1017 | ECO NUMBER: ECO-08-020204 | REV.: D | DATE: August 14, 2008 | SHEET: 2 of 3 |
|--|------------------------------|------------|--------------------------|------------------|

© 2004 -2008Tyco Electronics Corporation. All rights reserved.

If this document is printed it becomes uncontrolled. Check for the latest revision.

CUSTOMER DRAWING

Note 1: Adhesive Peel Strength

Polyolefin

Shrink a 6-inch length of size 1-1/2 inch tubing RNF-100 Type 2* on a glass-laminated plastic or metal tube, 1 inch in diameter, and approximately 1 foot long, with a Thermofit Model 500B Thermogun* or equivalent. Cool to room temperature, lightly abrade with No. 320 emery cloth, and wipe with MEK. Spiral wrap S-1017+ tape on the recovered tubing, with a 50% overlap. Place a strip of 3/4-inch-wide masking tape lengthwise on the adhesive tape to hold it in place and to provide unbonded ends to insert into the tensile tester.

Abrade and clean the inside surface of three 1-1/2 inch lengths of size 1-1/2 inch RNF-100 Type 2. Place them on the prepared mandrel so that they are about 1/2 inch apart, and shrink with the Thermogun. Place the assembly in an oven for 10 minutes at $150 \pm 3^{\circ}\text{C}$ ($302 \pm 5^{\circ}\text{F}$).

Cool to room temperature, and cut along one edge of the masking tape to remove the bonded assembly from the mandrel. Cut a 1-inch wide specimen from the center of each double thickness. Insert the unbonded ends in a tensile tester operating at 2 inches per minute. Make readings of peel strength at every 1/2 inch of jaw separation after 1 inch initial separation. The average of 5 readings shall define peel strength.

Polychloroprene

Repeat above procedure, except use NTFR* tubing.

Polyvinylchloride

Repeat above procedure, except use Thermofit PVC* tubing.

*Obtainable from Tyco Electronics/Raychem Corporation.
+S-1017 tape is made from the same lot of material as SAS-1017.

Tyco Electronics Corporation/Raychem reserves the right to amend this specification at any time. Users should evaluate the suitability of the product for their application.

| | | | | |
|--|------------------------------|------------|--------------------------|------------------|
| DOCUMENT NO.: SAS-XXX-XXX-1017 | ECO NUMBER: ECO-08-020204 | REV.: D | DATE: August 14, 2008 | SHEET: 3 of 3 |
|--|------------------------------|------------|--------------------------|------------------|

© 2004 -2008 Tyco Electronics Corporation. All rights reserved.

If this document is printed it becomes uncontrolled. Check for the latest revision.

Компания «Life Electronics» занимается поставками электронных компонентов импортного и отечественного производства от производителей и со складов крупных дистрибьюторов Европы, Америки и Азии.

С конца 2013 года компания активно расширяет линейку поставок компонентов по направлению коаксиальный кабель, кварцевые генераторы и конденсаторы (керамические, пленочные, электролитические), за счёт заключения дистрибьюторских договоров

Мы предлагаем:

- Конкурентоспособные цены и скидки постоянным клиентам.
- Специальные условия для постоянных клиентов.
- Подбор аналогов.
- Поставку компонентов в любых объемах, удовлетворяющих вашим потребностям.
- Приемлемые сроки поставки, возможна ускоренная поставка.
- Доставку товара в любую точку России и стран СНГ.
- Комплексную поставку.
- Работу по проектам и поставку образцов.
- Формирование склада под заказчика.
- Сертификаты соответствия на поставляемую продукцию (по желанию клиента).
- Тестирование поставляемой продукции.
- Поставку компонентов, требующих военную и космическую приемку.
- Входной контроль качества.
- Наличие сертификата ISO.

В составе нашей компании организован Конструкторский отдел, призванный помогать разработчикам, и инженерам.

Конструкторский отдел помогает осуществить:

- Регистрацию проекта у производителя компонентов.
- Техническую поддержку проекта.
- Защиту от снятия компонента с производства.
- Оценку стоимости проекта по компонентам.
- Изготовление тестовой платы монтаж и пусконаладочные работы.



Тел: +7 (812) 336 43 04 (многоканальный)

Email: org@lifeelectronics.ru