

## Posistor® For Inrush Current Suppression

### 1. Part Numbering (Part Number)

PT   GL   07   AS   121   M   0N51   B0  
 Product ID   Series   Dimensions   Temperature Characteristics   Resistance   Resistance Tolerance   Individual Specifications   Packaging

### 2. Ratings

| Bulk Part Number   | Max. voltage | *1 Resistance Value at+25°C | *2 Max. inrush Current             | *3 Max. applying time of inrush current |
|--------------------|--------------|-----------------------------|------------------------------------|---|
| Taping Part Number |              |                             |                                    |   |
| PTGL07AS121M0N51B0 | 280Vrms.     | 120Ω±20%                    | 6.0Arms<br>8.46(A <sub>0-P</sub> ) | Max.10msec.                             |
| PTGL07AS121M0N51A0 |              |                             |                                    |   |
| PTGL07AS181M0N51B0 |              | 180Ω±20%                    | 4.4Arms<br>6.22(A <sub>0-P</sub> ) |   |
| PTGL07AS181M0N51A0 |              |                             |                                    |   |
| PTGL07AS201M0N51B0 |              | 200Ω±20%                    | 4.0Arms<br>5.66(A <sub>0-P</sub> ) |   |
| PTGL07AS201M0N51A0 |              |                             |                                    |   |


\*1 The resist. value is measured at a point of max. 2mm from the end of lead crimp.

\*2 Shows the maximum inrush current value which be introduced into Posistor at operating temperature range.

\*3 Shows the maximum applying time of inrush current value at operating temperature range.

### 3. Dimensions (mm)


(Bulk type)



(Taping type : Shown in Taping specification.)


Note)

Some part of resin covering lead wire of Posistor may come off by some outside shock on the root of lead wire, but Posistor can be used normally for electrical and reliability characteristics.



## Taping Specification

### 1. Dimensions of Taping



| Item  | Code                   | Dimensions                | Note  |
|---|------------------------|---------------------------|---|
| Pitch of Component                                | P                      | 12.7                      | Tolerance is determined by $\Delta S$             |
| Pitch of Sprocket Hole                            | P0                     | $12.7 \pm 0.3$            |   |
| Lead Spacing                                      | F                      | $5.0^{+0.8}_{-0.3}$       |   |
| Length from Hole Center to Component              | P2                     | $6.35 \pm 1.3$            | Deviation in the feeling direction                |
| Length from Hole Center to Lead                   | P1                     | $3.85 \pm 0.8$            |   |
| Body Diameter                                     | D                      | Refer to "2.Dimensions"   |   |
| Body Thickness                                    | T                      | Refer to "2.Dimensions"   |   |
| Deviation along Tape. Left or Right               | $\Delta S$             | $0 \pm 1.5$               | Including the inclination caused by lead bending. |
| Carrier Tape Width                                | W                      | $18.0 \pm 0.5$            |   |
| Position of Sprocket Hole                         | W1                     | $9.0^{+0.5}_{-0.75}$      | Deviation of tape width.                          |
| Lead Distance between Reference and Bottom Planes | H0                     | $16.0 \pm 1.0$            |   |
|   | H2                     | 6.0 max.                  |   |
| Overflow of Lead                                  | l                      | -0.5 ~ +1.0               |   |
| Diameter of Sprocket Hole                         | D0                     | $4.0 \pm 0.2$             |   |
| Lead Diameter                                     | d                      | Refer to "2.Dimensions"   |   |
| Total Tape Thickness                              | t1                     | $0.6 \pm 0.3$             | t2 = 2.0 max.                                     |
| Deviation across Tape                             | $\Delta h1, \Delta h2$ | 1.5 max                   |   |
| Portion to cut in Case of Defect                  | L                      | $11.0^{+0}_{-2.0}$        |   |
| Hold Down Tape Width                              | W0                     | 11.0 min.                 |   |
| Hold Down Tape Position                           | W2                     | 4.0 max.                  |   |
| Coating Extension on Lead                         | e                      | Up to the center of crimp |   |

2. Splicing way of tape

2.1 Cohesive power of tape is over 2.94N at test condition as below figure.





Fig.1


2.2 Splicing of tape

a. When base tape is spliced :



- Base tape shall be spliced by cellophane tape
- Total tape thickness shall be less than 1.05mm

b. When adhesive tape is spliced :



- Adhesive tape shall be spliced with overlapping.
- Total tape thickness shall be less than 1.05mm

c. When both tape are spliced at a time :




Splicing tape  
(Base and adhesive tapes  
are inserted in a splicing tape.)

(in mm)

### 2.3 Packing specification (Ammo Pack).



The tape with Posistor is folded each 25 pitches and packed in zigzag into a packing case, when body of Posistor is piled on other body under it. Standard quantity in a case are 1000pcs..

#### The size of packing case



#### Packing way

Folding in Zigzag



When Posistor 's body is situated on your side, adhesive tape is situated the upside.

## Notice for use

 **Caution**

1. This product is designed for application which is used under ordinary environment.(room temperature, normal humidity, normal pressure) Do not expose this to the following environments, because all these factor can deteriorate the characteristic of this and can cause failure or burn out.
  - (1) Corrosive gas or deoxidizing gas (Cl<sub>2</sub>, H<sub>2</sub>S, NH<sub>3</sub>, SO<sub>x</sub>, NO<sub>x</sub> etc.)
  - (2) Volatile, flammable gas
  - (3) Dusty place
  - (4) Place in a vacuum, reducing or putting pressure
  - (5) Place in splashed water, or high humidity and dewing place
  - (6) Salt water, oil, chemical liquid and solvent
  - (7) Vibratile place
  - (8) Other place equivalent to the above
  
2. Limitation of Applications  
Please contact us before using our products for the under-mentioned applications requiring especially high reliability in order to prevent defects which might directly cause damage to other party's life body or property(listed below).
  - (1)Aircraft equipment (2)Aerospace equipment (3)Undersea equipment (4)Power plant control equipment
  - (5)Medical equipment (6)Transportation equipment(automobiles, trains, ships, etc.)
  - (7)Traffic signal equipment (8)Disaster prevention / Crime prevention equipment
  - (9)Data-processing equipment (10)Applications of similar complexity or with reliability requirements comparable to the applications listed in the above.
  
3. Be sure to provide an appropriate fail-safe function on your product to prevent a second damage that may be caused by the abnormal function or the failure of our product.

**Notice**

1. Do not apply abnormal voltage/current exceeding the specified maximum value. Because they may deteriorate or destroy PTC element.
2. Use this product within the specified temperature. A higher temperature may deteriorate the characteristic or material.
3. When this product is operated, temperature of some area may be over 100°C to 160°C. Please make sure that surrounding parts and inserting material can withstand the temperature. If the surrounding part and material is kept under such condition, they may be deteriorated or may produce harmful gas(Cl<sub>2</sub>, H<sub>2</sub>S, NH<sub>3</sub>, SO<sub>x</sub>, NO<sub>x</sub> etc.). And, such harmful gas may deteriorate the element.
4. The resin coating of this product is not for insulating purpose. Keep an adequate insulating distance to surrounding components.
5. This product does not have waterproof construction. A splashed water may cause failure mode such as deterioration of characteristic or current leak.  
So, Do NOT apply cleaning to immerse it into water or any solvent.
6. If you coat this product by resin, please evaluate the quality of this product before you use it.  
The stress of force which is caused by coating materials or heat cycles may cause failure mode such as deterioration of characteristic or current leak in worst case.
7. This product is using the solder of 221+/-5 °C of melting points, in order to connect ceramics with a lead wire. Do not heat up a terminal area of this product over 180 °C.
8. The ceramic element of this product is fragile, and care must be taken not to load a excessive pressforce or not to give a shock at handling. Such forces may cause cracking or chipping.

9. Do not apply an excessive force to the lead. Otherwise, it may cause break off the junction between lead and element, or may crack element. Therefore, hold of element side lead wire is recommended when lead wire is bent or cut.
10. When the lead of this product is soldered, pay attention as follows to avoid the decline of element characteristic or break down the element.
  - (1) Use Rosin type flux or non-activated flux(the content of chlorine shall be less than 0.2%)
  - (2) Do not dip the body into flux. (Flux shall be coated to lead wire only for soldering.)
  - (3) The pre-heat up should be conducted without melting the soldering of this product.
11. Do not apply tensile force or separating force to lead wire at soldering.
12. Do not touch the resin case by soldering iron. The soldering point shall be min. 5 mm away from the root of lead wire. Please solder the following conditions.
  - Iron Tip Temperature : 360 degree C max.
  - Soldering Time : 4 seconds max. / 1 terminal
  - Number of Soldering : 1
13. To keep solderability of product from declining, following storage condition is recommended.
  - (1) Storage condition Temperature : -10 to +40°C  
Humidity : less than 75%RH(not dewing condition)
  - (2) Term : Please use this product within 6 months after shipment by first-in and first-out stocking system.
  - (3) Handling after unpacking of the minimum package : Reseal it promptly or store it seal open inside a sealed container with a drying agent.
  - (4) Place : Do not store this product in corrosive gas(SO<sub>x</sub>,Cl etc) or under sun-light.

Компания «Life Electronics» занимается поставками электронных компонентов импортного и отечественного производства от производителей и со складов крупных дистрибьюторов Европы, Америки и Азии.

С конца 2013 года компания активно расширяет линейку поставок компонентов по направлению коаксиальный кабель, кварцевые генераторы и конденсаторы (керамические, пленочные, электролитические), за счёт заключения дистрибьюторских договоров

Мы предлагаем:

- Конкурентоспособные цены и скидки постоянным клиентам.
- Специальные условия для постоянных клиентов.
- Подбор аналогов.
- Поставку компонентов в любых объемах, удовлетворяющих вашим потребностям.
- Приемлемые сроки поставки, возможна ускоренная поставка.
- Доставку товара в любую точку России и стран СНГ.
- Комплексную поставку.
- Работу по проектам и поставку образцов.
- Формирование склада под заказчика.
- Сертификаты соответствия на поставляемую продукцию (по желанию клиента).
- Тестирование поставляемой продукции.
- Поставку компонентов, требующих военную и космическую приемку.
- Входной контроль качества.
- Наличие сертификата ISO.

В составе нашей компании организован Конструкторский отдел, призванный помогать разработчикам, и инженерам.

Конструкторский отдел помогает осуществить:

- Регистрацию проекта у производителя компонентов.
- Техническую поддержку проекта.
- Защиту от снятия компонента с производства.
- Оценку стоимости проекта по компонентам.
- Изготовление тестовой платы монтаж и пусконаладочные работы.



Тел: +7 (812) 336 43 04 (многоканальный)  
Email: org@lifeelectronics.ru