

RF Conductive Caulking Compound and Sealer

RF CONDUCTIVE CAULKING COMPOUND AND SEALER



Eccoshield VY-81 is a single-component electrically conductive non-hardening compound of metallic particles. It is similar to but different from our Eccoshield® VY product, in that the VY-81 has an increased volume resistivity (decreased conductivity). It also has a lower density than Eccoshield VY and is more cost effective to use per pound. Once applied, Eccoshield VY-81 assures long-term integrity of the shielding enclosure and will prevent corrosion in the contact area. Due to high tack and non-hardening characteristics, Eccoshield VY-81 will function under vibration and displacement due to temperature changes. It is fast and economical to use.

FEATURES AND BENEFITS

- maintains good shielding effectiveness due to non-hardening characteristic of material
- material can be applied using conventional caulking equipment

MARKETS

- Commercial Telecom
- Test and Measurement
- Security and Defense

SPECIFICATIONS

TYPICAL PROPERTIES	ECCOSHIELD VY-81
Service Temperature °C (°F)	-54 to 205 (-65 to 400)
Volume Resistivity Ohm-cm	0.01
Density g/cc	1.80
Shielding effectiveness dB	80 - 90
Length of 3mm diam. bead/lb, m (ft)	32 (105)

*Data for design engineer guidance only. Observed performance varies in application.
Engineers are reminded to test the material in application.*

APPLICATIONS

- Eccoshield VY-81 is specifically designed for use as a shielding effective material for EMI/RF protection on structures, cabinets, conduits, modules and components.
- Joints, seams, threads, cracks, and other RF leakage sources can be effectively plugged.

AVAILABILITY

- Eccoshield VY-81 is sold by the pound in one pound (16 oz.) jars.

INSTRUCTIONS FOR USE

- Eccoshield VY-81 can be used with conventional caulking equipment to develop fast and uniform-weight beads. It can also be applied by spatula, putty knife, plastic syringe applicators, or other suitable tools such as caulking guns. For spatula application, small amount of methyl ethyl ketone (MEK) can be added to adjust consistency.
- All surfaces for application should be prepared by removing rust, scale, non-conductive oxides and dirt. Wire brushing and/or solvent cleaning is usually adequate. Surfaces should be bright and electrically conductive.



Eccoshield® VY-81

- Apply Eccoshield VY-81 to the prepared surface using a syringe, caulking gun, or spatula. Lap joints may be made immediately. Excess and spillage may be collected and reused. Hardened or thick material can be reactivated by the addition of small amounts of methyl ketone.
- For cleanup, acetone or trichloroethylene are suitable.

Caution: Eccoshield VY-81 contains flammable solvents. Keep away from heat and open flames. When not in use, keep sealed to avoid evaporation. The handling of these products should present no problems if ordinary care is exercised to avoid breathing vapors, the skin is protected against contamination, swallowing is avoided, and eyes are protected.

RFP-DS-VY-81 031016

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies makes no warranties as to the fitness, merchantability, suitability or non-infringement of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2015 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights.

ООО "ЛайфЭлектроникс"

"LifeElectronics" LLC

ИНН 7805602321 КПП 780501001 Р/С 40702810122510004610 ФАКБ "АБСОЛЮТ БАНК" (ЗАО) в г.Санкт-Петербурге К/С 30101810900000000703 БИК 044030703

Компания «Life Electronics» занимается поставками электронных компонентов импортного и отечественного производства от производителей и со складов крупных дистрибуторов Европы, Америки и Азии.

С конца 2013 года компания активно расширяет линейку поставок компонентов по направлению коаксиальный кабель, кварцевые генераторы и конденсаторы (керамические, пленочные, электролитические), за счёт заключения дистрибуторских договоров

Мы предлагаем:

- Конкурентоспособные цены и скидки постоянным клиентам.
- Специальные условия для постоянных клиентов.
- Подбор аналогов.
- Поставку компонентов в любых объемах, удовлетворяющих вашим потребностям.
- Приемлемые сроки поставки, возможна ускоренная поставка.
- Доставку товара в любую точку России и стран СНГ.
- Комплексную поставку.
- Работу по проектам и поставку образцов.
- Формирование склада под заказчика.
- Сертификаты соответствия на поставляемую продукцию (по желанию клиента).
- Тестирование поставляемой продукции.
- Поставку компонентов, требующих военную и космическую приемку.
- Входной контроль качества.
- Наличие сертификата ISO.

В составе нашей компании организован Конструкторский отдел, призванный помочь разработчикам, и инженерам.

Конструкторский отдел помогает осуществить:

- Регистрацию проекта у производителя компонентов.
- Техническую поддержку проекта.
- Защиту от снятия компонента с производства.
- Оценку стоимости проекта по компонентам.
- Изготовление тестовой платы монтаж и пусконаладочные работы.



Тел: +7 (812) 336 43 04 (многоканальный)
Email: org@lifeelectronics.ru