



## 1544 Soldering Flux

### Activated Rosin Liquid Flux

#### Product Description

Kester 1544 Activated Rosin Liquid Flux is a homogeneous solution of high quality, purified Grade WW rosin blended into an alcohol solvent system. A very effective activating agent has been added to provide superior fluxing ability. 1544 is a liquid equivalent of Kester 44 Activated Rosin Core Solder. The desired flux activity and the amount of rosin residue are determined by the concentration (solids percentage) of the flux. 1544 has been developed for fluxing applications where non-activated and mildly activated rosin fluxes are too inactive to remove metal oxides, where proper and complete residue removal of potentially corrosive water-soluble organic acid flux is not possible, and where soldering of electronic assemblies requires instant wetting and excellent capillary flow. 1544 can be used for solder coating or tinning bare leads.

#### Performance Characteristics:

- High thermal stability
- Improves soldering performance
- Classified as ROM1 per J-STD-004

#### RoHS Compliance

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive, 2015/863 for the stated banned substances.

#### Physical Properties

**Specific Gravity:** 0.917-0.928  
Anton Paar DMA @ 25°C

**Percent Solids (typical):** 50%  
Tested to J-STD-004, IPC-TM-650, Method 2.3.34

**Flash Point:** 18°C (64°F)

#### Reliability Properties

**Copper Mirror Corrosion:** Moderate  
Tested to J-STD-004, IPC-TM-650, Method 2.3.32

**Silver Chromate:** Fail  
Tested to J-STD-004, IPC-TM-650, Method 2.3.33

**Fluorides by Spot Test:** Pass  
Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1

**Corrosion Test:** Low  
Tested to J-STD-004, IPC-TM-650, Method 2.6.15

**Chloride and Bromides:** 0.44%  
Tested to J-STD-004, IPC-TM-650, Method 2.3.35

## Flux Application

1544 can be applied by brush, dip or wave processes.

## Process Considerations

The optimum preheat temperature for most circuit assemblies is 90-105°C (194-221°F) as measured on the top or component side of the printed circuit board. Dwell time in the wave is typically 2-4 seconds for leaded soldering process and 4-8 seconds for a lead-free process. The wave soldering speed should be adjusted to accomplish the proper solder contact range. The next step will be to adjust the temperature settings for the preheat section to achieve the proper preheat temperatures range as measured on the topside of the circuit board.

## Flux Control

Specific gravity is normally the most reliable method to control the flux concentration of high solids rosin-based fluxes. To check concentration, a hydrometer should be used. Kester 104 Thinner is an appropriate solvent for diluting this activated rosin flux to the desired solids content and viscosity, and for restoring solvent loss through evaporation. The correct specific gravity range for 1544 is 0.917-0.928 (Anton Paar DMA @ 25°C).

## Cleaning

1544 residues are non-conductive, non-corrosive and do not require removal in most applications. If residue removal is required, call Kester Technical Support.

## Storage, Handling and Shelf Life

1544 is flammable. Store away from sources of ignition. Shelf life is 2 years from the date of manufacture when handled properly and held at 10-25°C (50-77°F).

## Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product.

Компания «Life Electronics» занимается поставками электронных компонентов импортного и отечественного производства от производителей и со складов крупных дистрибьюторов Европы, Америки и Азии.

С конца 2013 года компания активно расширяет линейку поставок компонентов по направлению коаксиальный кабель, кварцевые генераторы и конденсаторы (керамические, пленочные, электролитические), за счёт заключения дистрибьюторских договоров

Мы предлагаем:

- Конкурентоспособные цены и скидки постоянным клиентам.
- Специальные условия для постоянных клиентов.
- Подбор аналогов.
- Поставку компонентов в любых объемах, удовлетворяющих вашим потребностям.
- Приемлемые сроки поставки, возможна ускоренная поставка.
- Доставку товара в любую точку России и стран СНГ.
- Комплексную поставку.
- Работу по проектам и поставку образцов.
- Формирование склада под заказчика.
- Сертификаты соответствия на поставляемую продукцию (по желанию клиента).
- Тестирование поставляемой продукции.
- Поставку компонентов, требующих военную и космическую приемку.
- Входной контроль качества.
- Наличие сертификата ISO.

В составе нашей компании организован Конструкторский отдел, призванный помогать разработчикам, и инженерам.

Конструкторский отдел помогает осуществить:

- Регистрацию проекта у производителя компонентов.
- Техническую поддержку проекта.
- Защиту от снятия компонента с производства.
- Оценку стоимости проекта по компонентам.
- Изготовление тестовой платы монтаж и пусконаладочные работы.



Тел: +7 (812) 336 43 04 (многоканальный)

Email: [org@lifeelectronics.ru](mailto:org@lifeelectronics.ru)